

Technical Data Sheet

updated
checked

02.02.2017
02.02.2017

Product	Re-Jetflag GS PES-Fahnenstoff mit "INKTeX+® GS Ausrüstung" 6144RCGS made of REvive Polyester, because of the Recyling-process the degree of whiteness differs from production lot to production lot
Material	100% recycled Polyester
Stock widths	app. 320 cm
Making-up	rolled on paper cores
Packaging	wrapped with foil
Ecology	according to Öko-Tex Standard 100, product class IV
Ink-type	transfer printing, direct printing with dye-sub inks
Eigenschaften	Flame retardant

Weight				
acc. to DIN EN 12127	110.00	[g/m²]	+ - 5	[%]

Shrinkage

Heat Shrinkage, 195 °C, 90 sec, lengthwise				
acc. to PA0_13	-1.00	[%]	+ - 1	[%]
Heat Shrinkage, 195 °C, 90 sec, crosswise				
acc. to PA0_13	-1.00	[%]	+ - 1	[%]

Tearing strength

Elongation at 100 N, longitudinal direction				
acc. to DIN EN ISO 13934-1	5.00	[%]	+ - 20	[%]
Elongation at 100 N, cross direction				
acc. to DIN EN ISO 13934-1	20.00	[%]	+ - 20	[%]
Maximum tensile elongation, longitudinal direction				
acc. to DIN EN ISO 13934-1	30.00	[%]	+ - 20	[%]

Maximum tensile elongation, cross direction

acc. to DIN EN ISO 13934-1

50.00 [%]

+ - 20 [%]

Maximum tearing strength, longitudinal direction

acc. to DIN EN ISO 13934-1

min. 320.00 [N/5 cm]

Maximum tearing strength, cross direction

acc. to DIN EN ISO 13934-1

min. 540.00 [N/5 cm]

We do not accept liability for errors. Printing mistakes and changes are reserved.

Please pay attention to our general considerations regarding fabrication at www.g-o-friedrich.com

Page 2 / 2